



Characteristics and scope of application

- Filler metal for Alloy C4 and other NiCrMo-Alloys
- Recommended for dissimilar welds of wrought and cast grades of the above mentioned alloys to mild steels
- Excellent resistance against crevice and pitting attack

Standard designations

DIN EN ISO 18274	AWS A5.14	DIN Mat.-No.
S Ni 6455 (NiCr16Mo16Ti)	ERNiCrMo-7	2.4611

Typical chemical composition of filler metal

	C	Cr	Mo	Ni	Ti	Fe	W
Mass %	<0.01	16	16	Bal.	0.5	0.3	0.2

All weld metal properties (min. values at rt)

Heat treatment	Yield strength	Tensile strength	Elongation	Impact toughness	
	R _{p0.2}	R _m	A ₅	ISO-V	
as welded	400 MPa	690 MPa	35%	90 J	

Welding instructions

Polarity	Shielding gas acc. to AWS A5.32
DC / +	SG-A, SG-AHe, SG-A-G (He 30% - H 2% - C ~0.1)
DC / -	SG-A, SG-AHe, SG-AH (max. 5% H ₂)

Low heat input required. Stringer bead technique recommended.
Reducing shielding gases are preferable for welding of corrosion resistant alloys.

Base materials

2.4610 – NiMo16CSG-AH6Ti – Alloy C4 – UNS N06455

1.0345 - P235 GH - UNS K01501

Packaging (tolerances acc. to AWS A5.02)

Approvals on request

Diameter (in)		lbs/PU
1/16 - 1/8	x 36 in	11 / 22
0.8 / 1.0 / 1.2	BS 300 spool	33
1.6 / 2.4 / 3.2	K 415 / K 435 spool	55