



Characteristics and scope of application

- Filler metal for multi-layer and overlay welding primarily for repair work on cast iron
- Recommended for dissimilar welds of cast iron and mild steels

Standard designations

DIN EN ISO 1071	AWS 5.15	DIN Mat.-No.
S NiFe-1	ENiFe-CI	~ 2.4472

Typical chemical composition of filler metal

	C	Si	Mn	P	S	Fe	Ni	Cu
Mass %	0.05	0.1	0.8	< 0.01	< 0.01	Bal.	55	< 0.1

All weld metal properties (min. values at rt)

Heat treatment	Yield strength	Tensile strength	Elongation	Impact toughness	
	Rp0.2	R _m	A ₅	ISO-V	
as welded	42 ksi	61 ksi	6%		

Welding instructions

Polarity	Shielding gas acc. to AWS A5.32
DC / +	SG-A, M12
DC / -	SG-A, SG-AHe

Low heat input and preheating temperature according to fabrication guidelines of cast iron manufacturer, but not above 572°F. Interpass temperature approx. 122°F above preheating temperature.

Base materials
EN-GJL-250, EN-GJS-350-22

Packaging (tolerances acc. to AWS A5.02)

Approvals on request

Diameter (in)		lbs/PU
1/16 - 1/8	X 36 in	11 / 22
0.035 – 0.045	BS 300 spool	33
0.06 – 1/8	K 415 / K 435 spool	55